


BARI

RADICI
CARPET



STAINADVERSE



Costruzione	Construction	Technique de fabrication	Herstellungsverfahren
Tufting velluto 1/10"	Tufted cut pile 1/10"	Tufted velours 1/10"	Getufted velours 1/10"
Composizione	Composition	Composition	Polnutschicht
100% Poliammide	100% Polyamid	100% Polyamide	100% Polyamid
Sottofondo	Secondary backing	Dossier	Rückenausrüstung
Juta sintetica	Synthetic jute	Jute synthétique	SDR Textilrücken
Punti al m²	Stitches per m²	Touffes au m²	Knoten m²
± 146150	± 146150	± 146150	± 146150
Altezza pelo	Pile height	Hauteur du velours	Polhöhe
± 8.1 mm	± 8.1 mm	± 8.1 mm	± 8.1 mm
Altezza totale	Total height	Hauteur totale	Gesamthöhe
± 10.5 mm	± 10.5 mm	± 10.5 mm	± 10.5 mm
Peso fibra	Yarn weight	Poids du velours	Polgewicht
± 1050 g/m²	± 1050 g/m²	± 1050 g/m²	± 1050 g/m²
Peso totale	Total weight	Poids total	Gesamtgewicht
± 1970 g/m²	± 1970 g/m²	± 1970 g/m²	± 1970 g/m²
Larghezza rolo	Roll width	Largeur du rouleau	Breite
400 cm	400 cm	400 cm	400 cm
Famiglia tufting 1	Famiglia tufting 1	Famiglia tufting 1	Famiglia tufting 1



COMFORT: ★★★★★

BUSINESS WEARABILITY: ★★

DOMESTIC WEARABILITY: ★★★

Colour fastness to light	≥ 5	Thermal resistance m2 K/W	≤ 0,17
Insulation impact noise ΔLw	29 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,20		

This product is recyclable. For more information, please contact us at info@radicicarpet.it

Radici Pietro Industries & Brands Spa - 24026 Cazzano Sant'Andrea (BG) Italia - www.radicicarpet.it - info@radicicarpet.it

Radici Pietro I&B. reserves the right to modify the characteristics of the product while keeping the same technical properties

TSO2/2025