

CERVINO

(FLAT WOVEN)

RADICI
CARPET



COSTRUZIONE	CONSTRUCTION	TECHNIQUE DE FABRICATION	HERSTELLUNGSVERFAHREN
TESSUTO-RICCIO	WOVEN-LOOP PILE	TISSÉE-BOUCLÉ	GEWEBT-SCHLINGE
COMPOSIZIONE	COMPOSITION	COMPOSITION	POLNUTZSCHICHT
100% POLIAMMIDE 6 SD	100% POLYAMID 6 SD	100% POLYAMIDE 6 SD	100% POLYAMID 6 SD
SOTTOFONDO	SECONDARY BACKING	DOSSIER	RÜCKENAUSRÜSTUNG
JUTA SINTETICA	SYNTHETIC JUTE	JUTE SYNTHÉTIQUE	SDR TEXTILRUCKEN
PUNTI AL M ²	STITCHES PER M ²	TOUFFES AU M ²	KNOTEN M ²
± 164000	± 164000	± 164000	± 164000
ALTEZZA PELO	PILE HEIGHT	HAUTEUR DU VELOURS	POLHÖHE
± 2.0 mm	± 2.0 mm	± 2.0 mm	± 2.0 mm
ALTEZZA TOTALE	TOTAL HEIGHT	HAUTEUR TOTALE	GESAMTHÖHE
± 3.0 mm	± 3.0 mm	± 3.0 mm	± 3.0 mm
PESO FIBRA	YARN WEIGHT	POIDS DU VELOURS	POLGEWICHT
± 400 g/m ²	± 400 g/m ²	± 400 g/m ²	± 400 g/m ²
PESO TOTALE	TOTAL WEIGHT	POIDS TOTAL	GESAMTGEWICHT
± 1750 g/m ²	± 1750 g/m ²	± 1750 g/m ²	± 1750 g/m ²
LARGHEZZA ROTOLO	ROLL WIDTH	LARGEUR DU ROLEAU	BREITE
400 cm	400 cm	400 cm	400 cm



COMFORT: ★★☆☆☆

BUSINESS WEARABILITY: ★★☆☆

DOMESTIC WEARABILITY: ★★☆☆

Colour fastness to light	≥ 5	Thermal resistance m ² K/W	≤ 0,06
Insulation impact noise ΔL _w	16 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,15	Treatment	Soil Protection