

SYDNEY

RADICI
CARPET



Specifications and tolerances in according EN 1307

COSTRUZIONE	CONSTRUCTION	TECHNIQUE DE FABRICATION	HERSTELLUNGSVERFAHREN
TUFTING VELLUTO 1/10"	TUFTED CUT PILE 1/10"	TUFTED VELOURS 1/10"	GETUFTED VELOURS 1/10"
COMPOSIZIONE	COMPOSITION	COMPOSITION	POLNUTZSCHICHT
100% POLIAMMIDE SOLUTION DYED	100% POLYAMIDE SOLUTION DYED	100% POLYAMIDE SOLUTION DYED	100% POLYAMIDE SOLUTION DYED
SOTTOFONDO	SECONDARY BACKING	DOSSIER	RÜCKENAUSRÜSTUNG
JUTA SINTETICA	SYNTHETIC JUTE	JUTE SYNTHÉTIQUE	SDR TEXTILRUCKEN
PUNTI AL M ²	STITCHES PER M ²	TOUFFES AU M ²	KNOTEN M ²
± 220000	± 220000	± 220000	± 220000
ALTEZZA PELO	PILE HEIGHT	HAUTEUR DU VELOURS	POLHÖHE
± 5.5 mm	± 5.5 mm	± 5.5 mm	± 5.5 mm
ALTEZZA TOTALE	TOTAL HEIGHT	HAUTEUR TOTALE	GESAMTHÖHE
± 8.0 mm	± 8.0 mm	± 8.0 mm	± 8.0 mm
PESO FIBRA	YARN WEIGHT	POIDS DU VELOURS	POLGEWICHT
± 1220 g/m ²	± 1220 g/m ²	± 1220 g/m ²	± 1220 g/m ²
PESO TOTALE	TOTAL WEIGHT	POIDS TOTAL	GESAMTGEWICHT
± 2150 g/m ²	± 2150 g/m ²	± 2150 g/m ²	± 2150 g/m ²
LARGHEZZA ROTOLO	ROLL WIDTH	LARGEUR DU ROLEAU	BREITE
400 cm	400 cm	400 cm	400 cm
SYDNEY	SYDNEY	SYDNEY	SYDNEY



COMFORT: ★★★★★

BUSINESS WEARABILITY: ★★★

DOMESTIC WEARABILITY: ★★★

Colour fastness to light	≥ 5	Thermal resistance m2 K/W	0,13
Insulation impact noise ΔLw	30 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,20		