


VERONA

RADICI
CARPET

 EN14041	   
Specifications in according EN 1307 Tolerances in according Certification QBIUPEC For QBIUPEC certified characteristics see Website http://database.cstb.fr	



STAINADVERSE



CONSTRUZIONE	CONSTRUCTION	TECHNIQUE DE FABRICATION	HERSTELLUNGSVERFAHREN
TUFTING VELLUTO CROSS-OVER 1/10"	TUFTED CUT PILE CROSS-OVER 1/10"	TUFTED VELOURS CROSS-OVER 1/10"	GETUFTED VELOURS CROSS-OVER 1/10"
COMPOSIZIONE	COMPOSITION	COMPOSITION	POLNUTZSCHICHT
100% POLIAMMIDE 6.6	100% POLYAMID 6.6	100% POLYAMIDE 6.6	100% POLYAMID 6.6
SOTTOFONDO	SECONDARY BACKING	DOSSIER	RÜCKENAUSRÜSTUNG
JUTA SINTETICA	SYNTHETIC JUTE	JUTE SYNTHÉTIQUE	SDR TEXTILRUCKEN
PUNTI AL M ²	STITCHES PER M ²	TOUFFES AU M ²	KNOTEN M ²
± 193550	± 193550	± 193550	± 193550
ALTEZZA PELO	PILE HEIGHT	HAUTEUR DU VELOURS	POLHÖHE
± 5.7 mm	± 5.7 mm	± 5.7 mm	± 5.7 mm
ALTEZZA TOTALE	TOTAL HEIGHT	HAUTEUR TOTALE	GESAMTHÖHE
± 8.2 mm	± 8.2 mm	± 8.2 mm	± 8.2 mm
PESO FIBRA	YARN WEIGHT	POIDS DU VELOURS	POLGEWICHT
± 880 g/m ²	± 880 g/m ²	± 880 g/m ²	± 880 g/m ²
PESO TOTALE	TOTAL WEIGHT	POIDS TOTAL	GESAMTGEWICHT
± 1900 g/m ²	± 1900 g/m ²	± 1900 g/m ²	± 1900 g/m ²
LARGHEZZA ROTOLO	ROLL WIDTH	LARGEUR DU ROLEAU	BREITE
400 cm	400 cm	400 cm	400 cm
FAMIGLIA TUFTING 1	FAMIGLIA TUFTING 1	FAMIGLIA TUFTING 1	FAMIGLIA TUFTING 1



COMFORT: ★★★★★

BUSINESS WEARABILITY: ★★☆☆

DOMESTIC WEARABILITY: ★★★☆☆

Colour fastness to light	≥ 5	Thermal resistance m2 K/W	≤ 0,17
Insulation impact noise ΔLw	25 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,25		