

# PARMA

**RADICI**  
CARPET



**ECONYL®**

COSTRUZIONE	CONSTRUCTION	TECHNIQUE DE FABRICATION	HERSTELLUNGSVERFAHREN
TUFTING VELLUTO- FRISÉE 1/10"	TUFTED CUT PILE- FRISÉE 1/10"	TUFTED CUT-FRISÉE 1/10"	GETUFTED SCHNITT- FRISÉE 1/10"
COMPOSIZIONE	COMPOSITION	COMPOSITION	POLNUTZSCHICHT
100% POLIAMMIDE ECONYL	100% POLYAMIDE ECONYL	100% POLYAMIDE ECONYL	100% POLYAMID ECONYL
SOTTOFONDO	SECONDARY BACKING	DOSSIER	RÜCKENAUSRÜSTUNG
POLYFLEX	POLYFLEX	POLYFLEX	POLYFLEX
PUNTI AL M <sup>2</sup>	STITCHES PER M <sup>2</sup>	TOUFFES AU M <sup>2</sup>	KNOTEN M <sup>2</sup>
± 178000	± 178000	± 178000	± 178000
ALTEZZA PELO	PILE HEIGHT	HAUTEUR DU VELOURS	POLHÖHE
± 5.5 mm	± 5.5 mm	± 5.5 mm	± 5.5 mm
ALTEZZA TOTALE	TOTAL HEIGHT	HAUTEUR TOTALE	GESAMTHÖHE
± 6.2 mm	± 6.2 mm	± 6.2 mm	± 6.2 mm
PESO FIBRA	YARN WEIGHT	POIDS DU VELOURS	POLGEWICHT
± 1100 g/m <sup>2</sup>	± 1100 g/m <sup>2</sup>	± 1100 g/m <sup>2</sup>	± 1100 g/m <sup>2</sup>
PESO TOTALE	TOTAL WEIGHT	POIDS TOTAL	GESAMTGEWICHT
± 4800 g/m <sup>2</sup>	± 4800 g/m <sup>2</sup>	± 4800 g/m <sup>2</sup>	± 4800 g/m <sup>2</sup>
DIMENSIONI QUADROTTA	TILE SIZE	TAILLES DES DALLE	GESAMTGEWICHT
50x50 cm	50x50 cm	50x50 cm	50x50 cm
FAMIGLIA TUFTING 27	FAMIGLIA TUFTING 27	FAMIGLIA TUFTING 27	FAMIGLIA TUFTING 27



**BUSINESS WEARABILITY: ★★ ★**

Colour fastness to light	4- 5	Thermal resistance m <sup>2</sup> K/W	≤ 0,17
Insulation impact noise ΔLw	25 dB	Body voltage walking test kV	≤ 2