

PARMA

RADICI
CARPET



Specifications and tolerances in according EN 1307

ECONYL®

COSTRUZIONE	CONSTRUCTION	TECHNIQUE DE FABRICATION	HERSTELLUNGSVERFAHREN
TUFTING VELLUTO- FRISÉE 1/10"	TUFTED CUT PILE- FRISÉE 1/10"	TUFTED CUT-FRISÉE 1/10"	GETUFTED SCHNITT- FRISÉE 1/10"
COMPOSIZIONE	COMPOSITION	COMPOSITION	POLNUTZSCHICHT
100% POLIAMMIDE ECONYL SD	100% POLYAMIDE ECONYL SD	100% POLYAMIDE ECONYL SD	100% POLYAMID ECONYL SD
SOTTOFONDO	SECONDARY BACKING	DOSSIER	RÜCKENAUSRÜSTUNG
POLYFLEX	POLYFLEX	POLYFLEX	POLYFLEX
PUNTI AL M²	STITCHES PER M²	TOUFFES AU M²	KNOTEN M²
± 178000	± 178000	± 178000	± 178000
ALTEZZA PELO	PILE HEIGHT	HAUTEUR DU VELOURS	POLHÖHE
± 5.5 mm	± 5.5 mm	± 5.5 mm	± 5.5 mm
ALTEZZA TOTALE	TOTAL HEIGHT	HAUTEUR TOTALE	GESAMTHÖHE
± 6.2 mm	± 6.2 mm	± 6.2 mm	± 6.2 mm
PESO FIBRA	YARN WEIGHT	POIDS DU VELOURS	POLGEWICHT
± 1100 g/m²	± 1100 g/m²	± 1100 g/m²	± 1100 g/m²
PESO TOTALE	TOTAL WEIGHT	POIDS TOTAL	GESAMTGEWICHT
± 4800 g/m²	± 4800 g/m²	± 4800 g/m²	± 4800 g/m²
DIMENSIONI QUADROTTA	TILE SIZE	TAILLES DES DALLE	GESAMTGEWICHT
50x50 cm	50x50 cm	50x50 cm	50x50 cm
FAMIGLIA TUFTING 27	FAMIGLIA TUFTING 27	FAMIGLIA TUFTING 27	FAMIGLIA TUFTING 27



BUSINESS WEARABILITY: ★ ★ ★

Colour fastness to light	> 5	Thermal resistance m² K/W	≤ 0,17
Insulation impact noise ΔLw	25 dB	Body voltage walking test kV	≤ 2