


WINDSOR 38

RADICI
CARPET



Specifications and tolerances in according EN 1307



COSTRUZIONE	CONSTRUCTION	TECHNIQUE DE FABRICATION	HERSTELLUNGSVERFAHREN
MOQUETTE TESSUTA SUPERFICIE VELLUTO (2÷4 COLORI)	WOVEN CARPET CUT PILE (2÷4 COLOURS)	MOQUETTE TISSÉE À VELOURS COUPÉ (2÷4 COULEURS)	GEWEBT TEPPICH SCHNITTPOL (2÷4 FARBEN)
COMPOSIZIONE	COMPOSITION	COMPOSITION	POLNUTZSCHICHT
80% LANA 20% POLIAMMIDE	80% WOOL 20% POLYAMIDE	80% LAINE 20% POLYAMIDE	80% WOLLE 20% POLYAMID
SOTTOFONDO	SECONDARY BACKING	DOSSIER	RÜCKENAUSRÜSTUNG
JUTA NATURALE/SINTETICO	NATURAL JUTE/SYNTHETIC	JUTE NATUREL/SYNTHÉTIQUE	NATURJUTE/SYNTHETIK
PUNTI AL M ²	STITCHES PER M ²	TOUFFES AU M ²	KNOTEN M ²
± 121600	± 121600	± 121600	± 121600
ALTEZZA PELO	PILE HEIGHT	HAUTEUR DU VELOURS	POLHÖHE
± 7 mm	± 7 mm	± 7 mm	± 7 mm
ALTEZZA TOTALE	TOTAL HEIGHT	HAUTEUR TOTALE	GESAMTHÖHE
± 9 mm	± 9 mm	± 9 mm	± 9 mm
PESO FIBRA	YARN WEIGHT	POIDS DU VELOURS	POLGEWICHT
± 1480 g/m ²	± 1480 g/m ²	± 1480 g/m ²	± 1480 g/m ²
PESO TOTALE	TOTAL WEIGHT	POIDS TOTAL	GESAMTGEWICHT
± 2200 g/m ²	± 2200 g/m ²	± 2200 g/m ²	± 2200 g/m ²
LARGHEZZA ROTOLO	ROLL WIDTH	LARGEUR DU ROLEAU	BREITE
400 cm	400 cm	400 cm	400 cm
FAMIGLIA WILTON 80% LANA 20% POLIAMMIDE	FAMIGLIA WILTON 80% LANA 20% POLIAMMIDE	FAMIGLIA WILTON 80% LANA 20% POLIAMMIDE	FAMIGLIA WILTON 80% LANA 20% POLIAMMIDE



COMFORT: ★★★★★

BUSINESS WEARABILITY: ★★★

DOMESTIC WEARABILITY: ★★★

Colour fastness to light	≥ 5 (4 PASTEL SHADE)	Thermal resistance m2 K/W	≤ 0,17
Insulation impact noise ΔLw	30 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,22		